
BACURI

REQUIREMENT OF A PRESERVATIVE TREATMENT

Against dry wood borer attacks:	Does not require any preservative treatment
In case of temporary humidification risk:	Does not require any preservative treatment
In case of permanent humidification risk:	Use not recommended

DRYING

Possible drying schedule

Drying rate:	Normal to slow	Temperature (°C)			Air humidity (%)
		M.C. (%)	dry-bulb	wet-bulb	
Risk of distortion:	High risk	Green	42	39	82
Risk of casehardening:	No	50	48	43	74
Risk of checking:	High risk	40	48	43	74
Risk of collapse:	No	30	48	43	74
		15	54	46	63

This schedule is given for information only and is applicable to thickness < 38 mm.

It must be used in compliance with the code of practice.

For thickness from 38 to 75 mm , the air relative humidity should be increased by 5 % at each step.

For thickness over 75 mm , a 10 % increase should be considered.

Note: Must be dried slowly and carefully.

SAWING AND MACHINING

Blunting effect:	Fairly high
Sawteeth recommended:	Stellite-tipped
Cutting tools:	Tungsten carbide
Peeling:	Not recommended or without interest
Slicing:	Good
Note:	Requires power. Silica content is variable.

ASSEMBLING

Nailing / Screwing:	Good but pre-boring necessary
Gluing:	Correct (for interior only)

END-USES

Main known end-uses; they must to be implemented according to the code of practice.

Important remark: some end-uses are mentionned for information (traditional, regional or ancient end-uses).

Stairs (inside)

Flooring

Cabinetwork (high class furniture)

Current furniture or furniture components

Exterior joinery

Interior joinery

Heavy carpentry

Sliced veneer
