

Common name:	BREU
Family:	BURSERACEAE
Scientific name(s):	Protium spp.

LOG DESCRIPTION		WOOD DESCRIPTION	
Diameter:	from 40 to 60 cm	Colour:	Light brown
Thickness of sapwood:	from to cm	Sapwood:	Not demarcated
Floats:	yes	Texture:	Medium
Durability in forest :	Low (must be treated)	Grain:	Straight or interlocked
		Interlocked grain:	Slight
Note:	Presence of shakes in some logs. Heartwood light brown to pinkish brown.		

PHYSICAL PROPERTIES			MECHANICAL PROPERTIES		
Physical and mechanical properties are based on mature heartwood specimens. These properties can vary greatly depending on origin and growth conditions.					
	mean	standard deviation		mean	standard deviation
Density *:	0.64 g/cm ³	0.04			
Monnin hardness*:	2.7	0.5	Crushing strength *:	57 MPa	3
Coef of volumetric shrinkage:	0.57 %	0.06	Static bending strength *:	85 MPa	13
Total tangential shrinkage:	10.0 %	0.6	Modulus of elasticity *:	14350 MPa	510
Total radial shrinkage:	5.5 %	0.4			
Fibre saturation point:	28 %				
Stability:	Moderately stable		(* : at 12 % moisture content ; 1 MPa = 1 N/mm ²)		

NATURAL DURABILITY AND TREATABILITY

Fungi and termite resistance refers to end-uses under temperate climate.

Except for special comments on sapwood, natural durability is based on mature heartwood.

Sapwood must always be considered as non-durable against wood degrading agents.

Fungi:	Class 5 - not durable
Dry wood borers:	Susceptible; sapwood not or slightly demarcated (risk in all the wood)
Termites:	Class S - Susceptible
Treatability:	3 - poorly permeable
Biological hazard class*:	1 - not in ground contact, under cover (no dampness)

* ensured by natural durability (according EN standards).

COUNTRIES - LOCAL NAMES

Countries	Local names
Bolivia	CARANO
Brazil	ALMECEGA
Brazil	ARURU
Brazil	BREU
Colombia	ANIME
Colombia	CARANO
Colombia	CURRUCAY
Ecuador	ANIME BLANCO
French Guiana	ENCENS BLANC, GRIS, ROUGE
French Guiana	TINGUIMONI
Guyana	HAIWA
Guyana	KUROKAY
Guyana	POROKAY
Peru	COPAL-CASPI
Surinam	TINGUIMONI
Venezuela	ANIME
Venezuela	CARANO
Venezuela	AZUCARITO

BREU

REQUIREMENT OF A PRESERVATIVE TREATMENT

Against dry wood borer attacks: Requires appropriate preservative treatment
In case of temporary humidification risk: Use not recommended
In case of permanent humidification risk: Use not recommended

DRYING

Possible drying schedule

		Temperature (°C)			Air humidity (%)
		M.C. (%)	dry-bulb	wet-bulb	
Drying rate:	Normal to slow				
Risk of distortion:	High risk				
Risk of casehardening:	No				
Risk of checking:	Slight risk	Green	42	41	94
Risk of collapse:	No	50	48	43	74
		30	54	46	63
		20	60	51	62
		15	60	51	62

This shedule is given for information only and is applicable to thickness < 38 mm.

It must be used in compliance with the code of practice.

For thickness from 38 to 75 mm , the air relative humidity should be increased by 5 % at each step.

For thickness over 75 mm , a 10 % increase should be considered.

Note: Drying must be done with care in order to reduce the risks of distortion and prevent the extension of original shakes. Sometimes, risks of casehardening.

SAWING AND MACHINING

Blunting effect: Fairly high
Sawteeth recommended: Stellite-tipped
Cutting tools: Tungsten carbide
Peeling: Good
Slicing: Not recommended or without interest
Note: Logs should be debarked prior to sawing in order to avoid resin accumulation. Blunting effect quite important due to silica.

ASSEMBLING

Nailing / Screwing: Good but pre-boring necessary
Gluing: Correct
Note: Tends to split in nailing.

END-USES

Main known end-uses; they must to be implemented according to the code of practice.

Important remark: some end-uses are mentionned for information (traditional, regional or ancient end-uses).

Veneer for interior of plywood
Veneer for back or face of plywood
Boxes and crates
Current furniture or furniture components
Interior panelling
Formwork
Blockboard
Fiber or particle boards
